

ステンレス鋼母材組合せ別

2

溶接材料と母材の組合せ

母材	SUS304	SUS304L	SUS309S	SUS310S	SUS316	SUS316L	SUS317
SUS304	WEL 308 WEL TIG 308 WEL FCW 308T WEL MIG 308	WEL 308L WEL TIG 308L WEL FCW 308LT WEL MIG 308L	WEL 309 WEL TIG 309 WEL FCW 309T WEL MIG 309	WEL 309 WEL TIG 309 WEL FCW 309T WEL MIG 309	WEL 316 WEL TIG 316 WEL FCW 316T WEL MIG 316	WEL 316L WEL TIG 316L WEL FCW 316LT WEL MIG 316L	WEL 317 WEL TIG 317 WEL FCW 317T WEL MIG 317
SUS304L		WEL 308L WEL TIG 308L WEL FCW 308LT WEL MIG 308L	WEL 309L WEL TIG 309L WEL FCW 309LT WEL MIG 309L	WEL 309L WEL TIG 309L WEL FCW 309LT WEL MIG 309L	WEL 316L WEL TIG 316L WEL FCW 316LT WEL MIG 316L	WEL 316L WEL TIG 316L WEL FCW 316LT WEL MIG 316L	WEL 317L WEL TIG 317L WEL FCW 317LT WEL MIG 317L
SUS309S			WEL 309 WEL TIG 309 WEL FCW 309T WEL MIG 309	WEL 309 WEL TIG 309 WEL FCW 309T WEL MIG 309	WEL 309Mo WEL TIG 309Mo WEL FCW 309MoT WEL MIG 309Mo	WEL 309Mo WEL TIG 309Mo WEL FCW 309MoT WEL MIG 309Mo	WEL 309Mo WEL TIG 309Mo WEL FCW 309MoT WEL MIG 309Mo
SUS310S				WEL 310 WEL TIG 310 WEL FCW 310	WEL 309Mo WEL TIG 309Mo WEL FCW 309MoT WEL MIG 309Mo	WEL 309Mo WEL TIG 309Mo WEL FCW 309MoT WEL MIG 309Mo	WEL 309Mo WEL TIG 309Mo WEL FCW 309MoT WEL MIG 309Mo
SUS316					WEL 316 WEL TIG 316 WEL FCW 316T WEL MIG 316	WEL 316L WEL TIG 316L WEL FCW 316LT WEL MIG 316L	WEL 317L WEL TIG 317L WEL FCW 317LT WEL MIG 317L
SUS316L						WEL 316L WEL TIG 316L WEL FCW 316LT WEL MIG 316L	WEL 317L WEL TIG 317L WEL FCW 317LT WEL MIG 317L
SUS317							WEL 317 WEL TIG 317 WEL FCW 317T WEL MIG 317
SUS317L							
SUS321							
SUS347							
SUS403							
SUS405							
SUS410							
SUS430							

(注) 耐食等の使用環境条件によっては、他の溶接材料が選定されることがあります。

